

11/21/2023



Producer: Kendall Portsmouth

Material: 10/20

Specific.: EN12620 10 / 20 GC85/20 f1,5


TestOrder No	Seq	Date	Specifica tion	Moisture Content	Flakines s Index	40	31.5	25	20	16	14	12.5	10	8	6.3	5	4	2.8	2	1	0.063
tKWA/0113627	6	07-Nov-23	OK	2.2		100	100	100	90	62	40	25	4	0	0	0	0	0	0	0	0
tKWA/0113241	5	31-Oct-23	OK	2.6	12	100	100	100	93	68	48	29	6	1	0	0	0	0	0	0	0
tKWA/0112957	3	23-Oct-23	OK	2.1		100	100	100	89	50	31	17	4	1	1	1	1	0	0	0	0
tKWA/0112437	2	16-Oct-23	OK	2.8		100	100	100	92	56	35	21	5	1	1	1	0	0	0	0	0
tKWA/0112100	1	10-Oct-23	OK	2.6		100	100	100	93	54	34	19	3	0	0	0	0	0	0	0	0
tKWA/0111756	4	02-Oct-23	OK	2.1	9	100	100	100	87	47	29	16	3	0	0	0	0	0	0	0	0



Producer: Kendall Portsmouth

Material: 10/20

Specific.: EN12620 10 / 20 GC85/20 f1,5



	Specif...	Moisture Content	Flakiness Index	40	31.5	25	20	16	14	12.5	10	8	6.3	5	4	2.8	2	1	0.063
Count	6	6	2	6	6	6	6	6	6	6	6	6	6	6	6	6	6	6	6
Average		2.4	11	100	100	100	90	56	36	21	4	1	0	0	0	0	0	0	0
Upper Specification Limit			50	100	100		100				20				5				1.5
Lower Specification Limit				100	98		85				0				0				0
Max Value		2.8	12	100	100	100	93	68	48	29	6	1	1	1	1	0	0	0	0
Min Value		2.1	9	100	100	100	87	47	29	16	3	0	0	0	0	0	0	0	0