

DETERMINATION OF WATER CONTENT OF AGGREGATE

BS EN 1097-5: 2008 - Drying in a ventilated oven

REPORT NUMBER: C5013327 / 370211.3.1.1
SAMPLE NUMBER: See Below
CLIENT REF: See Below
DATE SAMPLED: 17/09/2025
SAMPLED BY: Ben Kynoch
DATE RECEIVED: 22/09/2025
DATE COMPLETED: 30/09/2025
TESTED BY: Jonathan Poole
TYPE OF SAMPLE: Disturbed
ENVIRONMENTAL CONDITIONS: Overcast

CLIENT: ERITH CONTRACTORS LTD
ADDRESS: Erith House, 7 Queen Street, Erith, Kent, DA8 1RP
SITE: SGN Littlehampton Holder Station
SUPPLIER:
MATERIAL: See Below
LOCATION: See Below
PREPARATION METHOD: BS EN 932-2
SAMPLING PLAN: CTS procedure TP41
METHOD OF SAMPLING: Method 4: Sampling material from heaps / stockpiles

RESULT Test Location: CTS Heathrow

SAMPLE NO.	CLIENT REF.	LOCATION	MATERIAL DESCRIPTION	NOMINAL SIZE	WATER CONTENT (%)	LOWER LIMIT	UPPER LIMIT
584553	Type1 Stockpile Bulk 2	Stockpile	Reddish brown slightly silty sandy GRAVEL	32	1.8	NA	NA

No specification requirements.

Remarks:

Test results reported relate only to the items tested.
This report shall not be reproduced except in full without approval of the Laboratory.
Opinions and interpretations expressed herein are outside the scope of UKAS Accreditation. The laboratory does not apply a conformity statement to test reports as standard, unless specifically requested by the customer.

Report Format: WC/TP16/Rep Issue 1 Rev 1 09/23

Unit 16 Britannia Ind Estate
Poyle Road
Colnbrook
SL3 0BH

www.constructiontesting.co.uk
END OF REPORT

For and on behalf of CTS
Shah Alam - Acting Laboratory Manager



Approved Signatory
Report date 30-Sep-25

Construction Testing Solutions Ltd.
Registered in England No. 05998333

Report version 1



4161